

View Online at <https://aerobasegroup.com/nsn/5315-00-459-7772>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

Between 0.490 inches and 0.510 inches

Pindiameter:

Between 0.1240 inches and 0.1250 inches

First End Taper Length:

Between 0.020 inches and 0.030 inches

Second End Taper Length:

Between 0.060 inches and 0.070 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

25.0 rockwell c and 33.0 rockwell c

First End Taper Angle:

Between 43.0 degrees and 47.0 degrees

Surface Finish:

32.0 microinches outside diameter

Second End Taper Angle:

Between 58.0 degrees and 62.0 degrees

Material:

Steel comp 410

Material Specification:

Ams 5613 assn standard single material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0