

View Online at <https://aerobasegroup.com/nsn/5315-00-558-0900>

First End Style:

Chamfered

Pinlength:

Between 0.700 inches and 0.720 inches

Pindiameter:

Between 0.1246 inches and 0.1248 inches

First End Taper Length:

Between 0.005 inches and 0.025 inches

Second End Relationship With First End:

Identical

Hardness Rating:

23.0 rockwell c and 32.0 rockwell c

First End Taper Angle:

45.0 degrees

Surface Finish:

125.0 microinches

Material:

Steel comp 416

Material Specification:

Qq-s-764 federal specification single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-f-14072, e300 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-f-14072 spec.