

View Online at <https://aerobasegroup.com/nsn/5315-00-664-1730>

First End Style:

Chamfered

Overall Length:

Between 3.255 inches and 3.275 inches

Diameter:

Between 0.498 inches and 0.499 inches

Effective Length:

Between 3.000 inches and 3.015 inches

Undercut Diameter:

Between 0.296 inches and 0.306 inches

Undercut Width:

Between 0.070 inches and 0.075 inches

Second Undercut Width:

Between 0.070 inches and 0.075 inches

Undercut Radius:

0.350 inches

First End Taper Length:

0.031 inches

Second End Relationship With First End:

Identical

Hardness Rating:

40.0 rockwell c and 45.0 rockwell c

First End Location:

Both ends

First End Taper Angle:

45.0 degrees

Material:

Steel

Surface Treatment:

Phosphate manganese

Surface Treatment Specification:

Mil-c-16232, type 1 military specification single treatment response

Style Designator:

Groove

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-c-16232 spec.