

View Online at <https://aerobasegroup.com/nsn/5315-00-685-0981>

**First End Style:**

Chamfered

**Pinlength:**

Between 9.484 inches and 9.516 inches

**Pindiameter:**

Between 0.12500 inches and 0.12503 inches

**First End Taper Length:**

Between 0.047 inches and 0.078 inches

**Second End Relationship With First End:**

Identical

**Hardness Rating:**

32.0 rockwell c and 36.0 rockwell c

**First End Taper Angle:**

Between 44.8 degrees and 45.3 degrees

**Surface Finish:**

32.0 microinches outside diameter

**Special Features:**

Magnetic particle inspect all over with mil-std-271, dry film lubricate electro film process

**Material:**

Steel comp 4140

**Material Specification:**

Aisi assn standard single material response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A212a0