

View Online at <https://aerobasegroup.com/nsn/5315-00-685-0982>

First End Style:

Chamfered

Pinlength:

Between 3.359 inches and 3.391 inches

Pindiameter:

Between 0.6251 inches and 0.6253 inches

First End Taper Length:

Between 0.047 inches and 0.078 inches

Second End Relationship With First End:

Identical

Hardness Rating:

32.0 rockwell c and 36.0 rockwell c

First End Taper Angle:

Between 44.8 degrees and 45.3 degrees

Surface Finish:

63.0 microinches outside diameter

Special Features:

Magnetic particle inspect all over with mil-std-271, dry film lubricate electro film process

Material:

Steel comp 4130

Material Specification:

Aisi assn standard single material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0