

View Online at <https://aerobasegroup.com/nsn/5315-00-761-3554>

**First End Style:**

Chamfered

**Pinlength:**

Between 0.740 inches and 0.760 inches

**Pindiameter:**

0.0940 inches

**First End Taper Length:**

Between 0.020 inches and 0.040 inches

**Second End Relationship With First End:**

Identical

**Hardness Rating:**

50.0 rockwell c and 60.0 rockwell c

**First End Taper Angle:**

Between 25.0 degrees and 35.0 degrees

**Surface Finish:**

63.0 microinches outside diameter

**Material:**

Steel comp 440c

**Material Specification:**

Qq-s-763 federal specification single material response

**Surface Treatment:**

Oxide and passivate

**Surface Treatment Specification:**

Mil-c-13924, class 2 military specification 1st treatment response and mil-f-14072, finish no e300 military specification 2nd treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A212a0

**Mil-std (military Standard):**

Mil-c-13924 spec.