

View Online at <https://aerobasegroup.com/nsn/5315-00-761-3554>

First End Style:

Chamfered

Pinlength:

Between 0.740 inches and 0.760 inches

Pindiameter:

0.0940 inches

First End Taper Length:

Between 0.020 inches and 0.040 inches

Second End Relationship With First End:

Identical

Hardness Rating:

50.0 rockwell c and 60.0 rockwell c

First End Taper Angle:

Between 25.0 degrees and 35.0 degrees

Surface Finish:

63.0 microinches outside diameter

Material:

Steel comp 440c

Material Specification:

Qq-s-763 federal specification single material response

Surface Treatment:

Oxide and passivate

Surface Treatment Specification:

Mil-c-13924, class 2 military specification 1st treatment response and mil-f-14072, finish no e300 military specification 2nd treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-c-13924 spec.