

View Online at <https://aerobasegroup.com/nsn/5315-00-770-4844>

First End Style:

Chamfered

Pinlength:

Between 0.540 inches and 0.560 inches

Pindiameter:

Between 0.25975 inches and 0.26025 inches

First End Taper Length:

Between 0.010 inches and 0.030 inches

Second End Relationship With First End:

Identical

Hardness Rating:

36.0 rockwell c and 42.0 rockwell c

First End Taper Angle:

45.0 degrees

Surface Finish:

32.0 microinches outside diameter

Material:

Steel comp 1095

Material Specification:

Ams 5132 assn standard single material response

Surface Treatment:

Oxide

Surface Treatment Specification:

Ams 2485 assn standard single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0