

View Online at <https://aerobasegroup.com/nsn/5315-00-805-3862>

First End Style:

Chamfered

Pinlength:

Between 0.615 inches and 0.635 inches

Pindiameter:

Between 0.1245 inches and 0.1255 inches

First End Taper Length:

Between 0.010 inches and 0.020 inches

Second End Relationship With First End:

Identical

Hardness Rating:

68.0 rockwell c and 72.0 rockwell c

First End Taper Angle:

Between 43.0 degrees and 47.0 degrees

Surface Finish:

125.0 microinches

Material:

Steel

Surface Treatment:

Phosphate manganese

Surface Treatment Specification:

Mil-I-644, cl 1 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-I-644 spec.