

View Online at <https://aerobasegroup.com/nsn/5315-00-805-3862>

**First End Style:**

Chamfered

**Pinlength:**

Between 0.615 inches and 0.635 inches

**Pindiameter:**

Between 0.1245 inches and 0.1255 inches

**First End Taper Length:**

Between 0.010 inches and 0.020 inches

**Second End Relationship With First End:**

Identical

**Hardness Rating:**

68.0 rockwell c and 72.0 rockwell c

**First End Taper Angle:**

Between 43.0 degrees and 47.0 degrees

**Surface Finish:**

125.0 microinches

**Material:**

Steel

**Surface Treatment:**

Phosphate manganese

**Surface Treatment Specification:**

Mil-I-644, cl 1 military specification single treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A212a0

**Mil-std (military Standard):**

Mil-I-644 spec.