

View Online at <https://aerobasegroup.com/nsn/5315-00-814-5227>

First End Style:

Chamfered

Pinlength:

Between 1.615 inches and 1.625 inches

Pindiameter:

Between 0.1242 inches and 0.1245 inches

First End Taper Length:

Between 0.020 inches and 0.040 inches

Second End Relationship With First End:

Identical

Hardness Rating:

38.0 rockwell c and 43.0 rockwell c

First End Taper Angle:

Between 44.0 degrees and 46.0 degrees

Surface Finish:

63.0 microinches outside diameter

Material:

Steel comp 4340

Material Specification:

Astm a322 assn standard single material response or astm a331 assn standard single material response

Surface Treatment:

Phosphate manganese or phosphate zinc

Surface Treatment Specification:

Mil-p-16232, ty m, cl 1 military specification 1st treatment response or mil-p-16232, ty aaus military specification 2nd treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A212a0

Mil-std (military Standard):

Mil-p-16232 spec.