

View Online at <https://aerobasegroup.com/nsn/5315-00-835-1241>

**First End Style:**

Chamfered

**Pinlength:**

Between 0.820 inches and 0.830 inches

**Pindiameter:**

Between 0.1900 inches and 0.1930 inches

**First End Taper Length:**

Between 0.020 inches and 0.030 inches

**Second End Relationship With First End:**

Identical

**Hardness Rating:**

74.0 rockwell a and 77.0 rockwell a

**First End Taper Angle:**

Between 20.0 degrees and 30.0 degrees

**Surface Finish:**

32.0 microinches outside diameter

**Material:**

Steel comp 6150

**Material Specification:**

Astm a322 assn standard single material response or astm a331 assn standard single material response

**Surface Treatment:**

Phosphate manganese or phosphate zinc

**Surface Treatment Specification:**

Mil-p-16232, ty m, cl 1 military specification 1st treatment response or mil-p-16232, ty z, cl 1 military specification 2nd treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli

**Fiig:**

A212a0

**Mil-std (military Standard):**

Mil-p-16232 spec.