

View Online at <https://aerobasegroup.com/nsn/5315-00-894-0588>

First End Style:

Chamfered

Pinlength:

Between 0.770 inches and 0.780 inches

Pindiameter:

Between 0.1230 inches and 0.1240 inches

First End Taper Length:

Between 0.010 inches and 0.030 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Identical

Hardness Rating:

45.0 rockwell c and 50.0 rockwell c

First End Taper Angle:

Between 44.5 degrees and 45.5 degrees

Surface Finish:

16.0 microinches outside diameter

Material:

Steel comp 416

Material Specification:

Qq-s-763 federal specification single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-s-5002 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-s-5002 spec.