

View Online at <https://aerobasegroup.com/nsn/5315-00-918-3177>

First End Style:

Chamfered

Pinlength:

Between 1.350 inches and 1.370 inches

Pindiameter:

Between 0.3105 inches and 0.3120 inches

First End Taper Length:

Between 0.010 inches and 0.030 inches

Second End Relationship With First End:

Identical

Hardness Rating:

32.0 rockwell c and 36.0 rockwell c

First End Taper Angle:

Between 44.5 degrees and 45.5 degrees

Surface Finish:

125.0 microinches

Material:

Steel comp 4130

Material Specification:

Mil-s-6758 military specification single material response

Surface Treatment:

Phosphate manganese

Surface Treatment Specification:

Mil-c-16232, tym, cl 1 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-s-6758 spec.