

View Online at <https://aerobasegroup.com/nsn/5315-00-918-3263>

First End Style:

Chamfered

Pinlength:

Between 0.610 inches and 0.630 inches

Pindiameter:

Between 0.2505 inches and 0.2510 inches

First End Taper Length:

Between 0.030 inches and 0.050 inches

Second End Relationship With First End:

Identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

First End Taper Angle:

Between 44.5 degrees and 45.5 degrees

Material:

Steel comp 4130

Material Specification:

Mil-s-6758 military specification single material response

Surface Treatment:

Phosphate manganese

Surface Treatment Specification:

Mil-c-16232, tym, cl 2 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-s-6758 spec.