

View Online at <https://aerobasegroup.com/nsn/5315-00-953-6077>

First End Style:

Chamfered

Second End Style:

Radius

Pinlength:

Between 0.740 inches and 0.760 inches

Pindiameter:

Between 0.1259 inches and 0.1261 inches

Second End Corner Radius:

0.041 inches

First End Taper Length:

0.158 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Not identical

Hardness Rating:

47.0 rockwell c and 58.0 rockwell c

Shear Strength:

3200 double pound

First End Taper Angle:

Between 4.0 degrees and 16.0 degrees

Surface Finish:

16.0 microinches outside diameter

Special Features:

Radius end may be chamfered 25 deg

Material:

Steel

Material Specification:

66 federal standard single material response

Surface Treatment:

Phosphate zinc

Surface Treatment Specification:

Mil-c-16232, ty2 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-c-16232 spec.