

View Online at <https://aerobasegroup.com/nsn/5315-00-953-6077>

**First End Style:**

Chamfered

**Second End Style:**

Radius

**Pinlength:**

Between 0.740 inches and 0.760 inches

**Pindiameter:**

Between 0.1259 inches and 0.1261 inches

**Second End Corner Radius:**

0.041 inches

**First End Taper Length:**

0.158 inches

**Features Provided:**

Casehardened

**Second End Relationship With First End:**

Not identical

**Hardness Rating:**

47.0 rockwell c and 58.0 rockwell c

**Shear Strength:**

3200 double pound

**First End Taper Angle:**

Between 4.0 degrees and 16.0 degrees

**Surface Finish:**

16.0 microinches outside diameter

**Special Features:**

Radius end may be chamfered 25 deg

**Material:**

Steel

**Material Specification:**

66 federal standard single material response

**Surface Treatment:**

Phosphate zinc

**Surface Treatment Specification:**

Mil-c-16232, ty2 military specification single treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A212a0

**Mil-std (military Standard):**

Mil-c-16232 spec.