

View Online at <https://aerobasegroup.com/nsn/5315-00-971-7413>

First End Style:

Chamfered

Overall Length:

Between 0.990 inches and 1.010 inches

Diameter:

Between 0.2494 inches and 0.2497 inches

Effective Length:

Between 0.760 inches and 0.765 inches

Undercut Diameter:

Between 0.182 inches and 0.187 inches

Undercut Width:

Between 0.034 inches and 0.037 inches

Second Undercut Width:

Between 0.034 inches and 0.037 inches

First End Taper Length:

Between 0.005 inches and 0.025 inches

Second End Relationship With First End:

Identical

Hardness Rating:

55.0 rockwell c and 60.0 rockwell c

First End Location:

Both ends

First End Taper Angle:

Between 40.0 degrees and 50.0 degrees

Surface Finish:

32.0 microinches outside diameter

Material:

Steel comp 4140

Material Specification:

Astm a322 assn standard single material response or a331 assn standard single material response

Surface Treatment:

Phosphate

Surface Treatment Specification:

Mil-p-16232, ty m, cl 2 military specification single treatment response

Style Designator:

Groove

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-p-16232 spec.