

View Online at <https://aerobasegroup.com/nsn/5315-00-971-8350>

First End Style:

Chamfered

Second End Style:

Radius

Pinlength:

Between 2.990 inches and 3.010 inches

Pindiameter:

Between 0.3751 inches and 0.3753 inches

Second End Corner Radius:

Between 0.063 inches and 0.167 inches

First End Taper Length:

0.664 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Not identical

Hardness Rating:

47.0 rockwell c and 58.0 rockwell c

Shear Strength:

28000 double pound

First End Taper Angle:

Between 4.0 degrees and 16.0 degrees

Surface Finish:

16.0 microinches outside diameter

Special Features:

Radius end may be chamfered 25.0 degrees

Material:

Steel

Material Specification:

Astm a29 assn standard single material response

Surface Treatment:

Phosphate zinc

Surface Treatment Specification:

Dod-p-16232 ty z cl 2 national specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0