

View Online at <https://aerobasegroup.com/nsn/5315-00-989-9230>

First End Style:

Chamfered

Second End Style:

Radius

Pinlength:

Between 0.365 inches and 0.385 inches

Pindiameter:

Between 0.0782 inches and 0.0784 inches

Second End Corner Radius:

Between 0.008 inches and 0.016 inches

First End Taper Length:

Between 0.068 inches and 0.096 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

Shear Strength:

700 double pounds per square inch

First End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Surface Finish:

125.0 microinches both ends

Special Features:

Radius end may be chamfered 25 deg

Material:

Steel comp 410 or steel comp 416

Material Specification:

66 federal standard all material responses

Surface Treatment:

Passivate

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0