

View Online at <https://aerobasegroup.com/nsn/5315-01-008-9496>

First End Style:

Chamfered

Pinlength:

Between 0.450 inches and 0.470 inches

Pindiameter:

Between 0.18725 inches and 0.18775 inches

First End Taper Length:

Between 0.050 inches and 0.070 inches

Second End Relationship With First End:

Identical

Hardness Rating:

40.0 rockwell c and 45.0 rockwell c

Criticality Code Justification:

Achu

Surface Finish:

32.0 microinches

Material:

Steel comp 4130

Material Specification:

Ams 6370 assn standard single material response

Surface Treatment:

Oxide

Surface Treatment Specification:

Ams 2485 assn standard single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0