

View Online at <https://aerobasegroup.com/nsn/5315-01-019-2764>

**First End Style:**

Chamfered

**Pinlength:**

Between 1.990 inches and 2.010 inches

**Pindiameter:**

Between 0.2501 inches and 0.2503 inches

**First End Taper Length:**

Between 0.031 inches and 0.062 inches

**Features Provided:**

Casehardened

**Second End Relationship With First End:**

Identical

**Hardness Rating:**

36.0 rockwell c and 40.0 rockwell c

**Shear Strength:**

10000 double pounds per square inch

**First End Taper Angle:**

Between 8.0 degrees and 25.0 degrees

**Surface Finish:**

16.0 microinches outside diameter

**Material:**

Steel

**Surface Treatment:**

Phosphate zinc

**Surface Treatment Specification:**

Mil-c-16232, tyz, cl 2 military specification single treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A212a0

**Mil-std (military Standard):**

Mil-c-16232 spec.