

View Online at <https://aerobasegroup.com/nsn/5315-01-019-2764>

First End Style:

Chamfered

Pinlength:

Between 1.990 inches and 2.010 inches

Pindiameter:

Between 0.2501 inches and 0.2503 inches

First End Taper Length:

Between 0.031 inches and 0.062 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

Shear Strength:

10000 double pounds per square inch

First End Taper Angle:

Between 8.0 degrees and 25.0 degrees

Surface Finish:

16.0 microinches outside diameter

Material:

Steel

Surface Treatment:

Phosphate zinc

Surface Treatment Specification:

Mil-c-16232, tyz, cl 2 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-c-16232 spec.