

View Online at <https://aerobasegroup.com/nsn/5315-01-049-8321>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

0.312 inches

Pindiameter:

Between 0.1248 inches and 0.1253 inches

First End Taper Length:

Between 0.016 inches and 0.041 inches

Second End Taper Length:

0.049 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 42.0 rockwell c

Shear Strength:

1800 double pounds per square inch

First End Taper Angle:

10.0 degrees

Second End Taper Angle:

25.0 degrees

Special Features:

Small end may be 0.016 in. Min 0.041 in. Maximum radius in lieu of chanfer

Material:

Steel comp 410 or steel comp 416

Material Specification:

Fed standard 66 federal standard all material responses

Surface Treatment:

Passivate

Surface Treatment Specification:

Qq-p-35 federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0