

View Online at <https://aerobasegroup.com/nsn/5315-01-078-3631>

First End Style:

Square

Pinlength:

Between 0.722 inches and 0.732 inches

Pindiameter:

Between 0.1220 inches and 0.1230 inches

Second End Relationship With First End:

Identical

Hardness Rating:

57.0 rockwell c and 60.0 rockwell c

Surface Finish:

32.0 microinches outside diameter

Material:

Steel comp 440c

Surface Treatment:

Passivate

Surface Treatment Specification:

Sps-209 method 1 fscm 99643 mfr ref single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0