

View Online at <https://aerobasegroup.com/nsn/5315-01-083-1669>

First End Style:

Chamfered

Pinlength:

Between 1.250 inches and 1.260 inches

Pindiameter:

Between 0.1797 inches and 0.1800 inches

First End Taper Length:

Between 0.010 inches and 0.020 inches

Second End Relationship With First End:

Identical

Hardness Rating:

30.0 rockwell c and 34.0 rockwell c

First End Taper Angle:

45.0 degrees

Surface Finish:

63.0 microinches outside diameter

Material:

Steel comp 4130

Material Specification:

Mil-s-6758, cond f-4 military specification single material response

Surface Treatment:

Cadmium and chromate or phosphate zinc

Surface Treatment Specification:

Qq-p-416, type 2 cl 3 federal specification 1st treatment response or dod-p-16232, ty z cl 3 mfr ref 2nd treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-s-6758 spec.