

View Online at <https://aerobasegroup.com/nsn/5315-01-102-5732>

First End Style:

Square

Diameter:

Between 0.247 inches and 0.248 inches

Effective Length:

Between 0.906 inches and 0.911 inches

Undercut Diameter:

Between 0.182 inches and 0.187 inches

Undercut Width:

Between 0.027 inches and 0.030 inches

Second Undercut Width:

Between 0.027 inches and 0.030 inches

Second End Relationship With First End:

Identical

Hardness Rating:

40.0 rockwell c and 48.0 rockwell c

First End Location:

Both ends

Surface Finish:

63.0 microinches outside diameter

Material:

Steel comp 630

Material Specification:

Ams 5643 assn standard single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Qq-p-35, type 1 or type 2 or type 3 federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0