

View Online at <https://aerobasegroup.com/nsn/5315-01-104-6898>

First End Style:

Chamfered

Pinlength:

Between 1.128 inches and 1.132 inches

Pindiameter:

Between 0.0600 inches and 0.0620 inches

First End Taper Length:

0.010 inches

Second End Relationship With First End:

Identical

Hardness Rating:

57.0 rockwell c and 59.0 rockwell c

First End Taper Angle:

45.0 degrees

Material:

Steel comp 440c

Material Specification:

Qq-s-763 federal specification single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-s-5002 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-s-5002 spec.