

View Online at <https://aerobasegroup.com/nsn/5315-01-148-3729>

First End Style:

Chamfered

Second End Style:

Radius

Pinlength:

0.500 inches

Pindiameter:

Between 0.1251 inches and 0.1253 inches

Second End Corner Radius:

0.046 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

60.0 rockwell c and 62.0 rockwell c

Shear Strength:

144000 single pounds per square inch

First End Taper Angle:

Between 5.0 degrees and 10.0 degrees

Surface Finish:

32.0 microinches outside diameter

Material:

Steel

Surface Treatment:

Phosphate manganese and lubricant or oxide

Surface Treatment Specification:

Dod-p-16232 type m, class 1 military specification 1st treatment response and mil-c-16173 grade 4 military specification 2nd treatment response or mil-c-13924 class 1 military specification 3rd treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-c-16173 spec.