

View Online at <https://aerobasegroup.com/nsn/5315-01-181-8162>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

1.500 inches

Pindiameter:

0.5010 inches

First End Taper Length:

0.500 inches

Second End Taper Length:

0.060 inches

Second End Relationship With First End:

Not identical

First End Taper Angle:

7.0 degrees

Second End Taper Angle:

45.0 degrees

Special Features:

Heat treatment: case harden 0.15 min depth quench and temper; hardness : surface-81.0 ra min, core 47/58 rc

Material:

Steel comp 4140 or steel comp 8640

Material Specification:

Astma322 assn standard 1st material response or astma331 assn standard 2nd material response

Surface Treatment:

Cadmium

Surface Treatment Specification:

Qq-p-416 type 2, class 3 federal specification 1st treatment response or mil-c-81562 type 2, class 3 federal specification 2nd treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0