

View Online at <https://aerobasegroup.com/nsn/5315-01-189-3499>

First End Style:

Chamfered

Pinlength:

0.250 inches

Pindiameter:

Between 0.1240 inches and 0.1243 inches

First End Taper Length:

Between 0.104 inches and 0.114 inches

Second End Relationship With First End:

Identical

Hardness Rating:

55.0 rockwell c and 60.0 rockwell c

First End Taper Angle:

10.0 degrees

Surface Finish:

63.0 microinches chamfered end

Special Features:

Caseharden

Material:

Steel comp 440c

Material Specification:

Ams 5630 assn standard single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Sp-151 fscm 66503 mfr ref single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0