

View Online at <https://aerobasegroup.com/nsn/5315-01-202-8530>

First End Style:

Square

Pinlength:

Between 0.750 inches and 0.780 inches

Pindiameter:

Between 0.3735 inches and 0.3740 inches

Second End Relationship With First End:

Identical

Hardness Rating:

31.0 rockwell c and 39.0 rockwell c

Special Features:

Finish dry film lubricant 0.0001 in. Min and 0.0003 in. Maximum thickness per ems52402, type 1, cl a

Material:

Steel comp 630

Material Specification:

Ams 5643 assn standard single material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0