

View Online at <https://aerobasegroup.com/nsn/5315-01-223-4933>

First End Style:

Chamfered

Second End Style:

Square

Pinlength:

Between 0.655 inches and 0.665 inches

Pindiameter:

Between 0.1259 inches and 0.1261 inches

First End Taper Length:

Between 0.060 inches and 0.080 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

First End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Surface Finish:

16.0 microinches

Material:

Steel comp 410 or steel comp 416

Material Specification:

Qq-s-763 federal specification all material responses

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-f-14072 e300 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-f-14072 spec.