

View Online at <https://aerobasegroup.com/nsn/5315-01-251-9722>

First End Style:

Square

Pinlength:

22.0 millimeters

Pindiameter:

3.35 millimeters

Cubic Measure:

246.895 cubic millimeters

Second End Relationship With First End:

Identical

Special Features:

Material is carbon, cold rolled, killed, and spheroidized; heat treatment=harden at 840 deg. C. In a carbonitriding atmosphere for 40 min., oil quench, temper 1 hr. Min. To rh a72-75

Material:

Steel comp 1055 or steel comp 1060

Material Specification:

Astm-a108 assn standard single material response or astm-a568, (s1 0.15-0.30%), grain size 5-7 assn standard single material response

Surface Treatment:

Phosphate manganese

Surface Treatment Specification:

Mil-p-16232, type m, class 1 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A212a0

Mil-std (military Standard):

Mil-p-16232 spec.