

View Online at <https://aerobasegroup.com/nsn/5315-01-251-9723>

First End Style:

Square

Pinlength:

7.35 millimeters

Pindiameter:

1.247 millimeters

Cubic Measure:

11.42931 cubic millimeters

Second End Relationship With First End:

Identical

Special Features:

Material is carbon, cold rolled, killed, spheroidized; heat treatment: harden at 840 deg. C. In a carbonitridingatmosphere for 40 min., oil quench, temper 1 hr. Min. To rh a 72-75

Material:

Steel comp 1060 or steel comp 1055 or steel comp 1065

Material Specification:

Astm-a568 assn standard single material response or astm-a108 assn standard single material response

Surface Treatment:

Phosphate

Surface Treatment Specification:

Mil-p-16232, type m, class 1 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A212a0

Mil-std (military Standard):

Mil-p-16232 spec.