

View Online at <https://aerobasegroup.com/nsn/5315-01-251-9723>

**First End Style:**

Square

**Pinlength:**

7.35 millimeters

**Pindiameter:**

1.247 millimeters

**Cubic Measure:**

11.42931 cubic millimeters

**Second End Relationship With First End:**

Identical

**Special Features:**

Material is carbon, cold rolled, killed, spheroidized; heat treatment: harden at 840 deg. C. In a carbonitridingatmosphere for 40 min., oil quench, temper 1 hr. Min. To rh a 72-75

**Material:**

Steel comp 1060 or steel comp 1055 or steel comp 1065

**Material Specification:**

Astm-a568 assn standard single material response or astm-a108 assn standard single material response

**Surface Treatment:**

Phosphate

**Surface Treatment Specification:**

Mil-p-16232, type m, class 1 military specification single treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli

**Fiig:**

A212a0

**Mil-std (military Standard):**

Mil-p-16232 spec.