

View Online at <https://aerobasegroup.com/nsn/5315-01-259-6464>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

Between 0.240 inches and 0.260 inches

Pindiameter:

Between 0.1251 inches and 0.1253 inches

First End Taper Length:

Between 0.016 inches and 0.041 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

First End Taper Angle:

Between 20.0 degrees and 30.0 degrees

Second End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Material:

Steel comp 416

Material Specification:

Astm a582 assn standard single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Astm a380 assn standard single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0