

View Online at <https://aerobasegroup.com/nsn/5315-01-302-6076>

**First End Style:**

Radius

**Pinlength:**

Between 1.710 inches and 1.715 inches

**Pindiameter:**

Between 0.6215 inches and 0.6230 inches

**First End Corner Radius:**

0.040 inches

**Second End Relationship With First End:**

Identical

**Special Features:**

Within half hour after plating, pin shall be baked for a of twelve hours at 350.0 degrees to 400.0 degrees fahrenheit to provide hydrogen embrittlement relief; apply solid dry film lubricant per ef 98. Edo report 5370: 0.0003 - 0.0005 thick per surface over dimensions shown

**Material:**

Steel comp xm-13

**Material Specification:**

Ams 5629, cond h-1000 assn standard single material response

**Surface Treatment:**

Chromium

**Surface Treatment Specification:**

Qq-c-320, class 2d, 0.0002 - 0.0004 thickness federal specification single treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A212a0