

View Online at <https://aerobasegroup.com/nsn/5315-01-302-9530>

First End Style:

Radius

Pinlength:

Between 2.450 inches and 2.455 inches

Pindiameter:

Between 0.6215 inches and 0.6230 inches

First End Corner Radius:

0.040 inches

Second End Relationship With First End:

Identical

Special Features:

Within half hour after plating, pin shall be baked for a of twelve hours at 350.0 degrees to 400.0 degrees fahrenheit to provide hydrogen embrittlement relief; apply solid dry film lubricant per ef 98. Edo report 5370 0.0003 - 0.0005 thick per surface over dimensions shown

Material:

Steel comp xm-13

Material Specification:

Ams 5629, cond h-1000 assn standard single material response

Surface Treatment:

Chromium

Surface Treatment Specification:

Qq-c-320, class 2d, 0.0002 - 0.0004 thickness federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0