

View Online at <https://aerobasegroup.com/nsn/5315-01-303-3959>

First End Style:

Radius

Pinlength:

Between 2.610 inches and 2.620 inches

Pindiameter:

Between 0.4970 inches and 0.4980 inches

First End Corner Radius:

0.040 inches

Second End Relationship With First End:

Identical

Special Features:

Within half hour after plating, pin shall be baked for a of 12 hours at 350.0 400.0 degrees fahrenheit to provide hydrogen embrittlement relief; apply solid dry film lubricant per ef 98. Edo report 5370: 0.0003-0.0005 thick per surface over dimensions shown

Material:

Steel

Material Specification:

Mil-s-8844, 300m cl 3 military specification single material response

Surface Treatment:

Nickel and chromium

Surface Treatment Specification:

Qq-n-290, class 1 grade a 0.0002-0.0004 thickness federal specification single treatment response and qq-c-320, class 2d 0.0002-0.0004 thickness federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-s-8844 spec.