

View Online at <https://aerobasegroup.com/nsn/5315-01-303-3959>

**First End Style:**

Radius

**Pinlength:**

Between 2.610 inches and 2.620 inches

**Pindiameter:**

Between 0.4970 inches and 0.4980 inches

**First End Corner Radius:**

0.040 inches

**Second End Relationship With First End:**

Identical

**Special Features:**

Within half hour after plating, pin shall be baked for a of 12 hours at 350.0 400.0 degrees fahrenheit to provide hydrogen embrittlement relief; apply solid dry film lubricant per ef 98. Edo report 5370: 0.0003-0.0005 thick per surface over dimensions shown

**Material:**

Steel

**Material Specification:**

Mil-s-8844, 300m cl 3 military specification single material response

**Surface Treatment:**

Nickel and chromium

**Surface Treatment Specification:**

Qq-n-290, class 1 grade a 0.0002-0.0004 thickness federal specification single treatment response and qq-c-320, class 2d 0.0002-0.0004 thickness federal specification single treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A212a0

**Mil-std (military Standard):**

Mil-s-8844 spec.