

View Online at <https://aerobasegroup.com/nsn/5315-01-322-4035>

End Application:

Oa15686 mk26 mod0 gmls

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 42.0 rockwell c

Surface Finish:

16.0 microinches

Material:

Steel comp 416 or steel comp 410

Material Specification:

Aisi 416, uns s41600 assn standard 1st material response or aisi 410 assn standard 2nd material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Qq-p-35 federal specification 1st treatment response or astm a380 assn standard 2nd treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0