

View Online at <https://aerobasegroup.com/nsn/5315-01-329-4858>

**First End Style:**

Chamfered

**Head Length:**

33.0 millimeters

**Under Head Length:**

91.0 millimeters

**First Step Diameter:**

12.6 millimeters

**First Step Length:**

40.0 millimeters

**Second Step Diameter:**

10.0 millimeters

**Second Step Length:**

51.0 millimeters

**Head Width:**

21.5 millimeters

**End Application:**

RECO-IL-AMP-LIFI

**First End Taper Length:**

2.0 millimeters

**First End Taper Angle:**

45.0 degrees

**Special Features:**

Calc. Material: classification and inspection of investment casting will be per class 3, grade c; heat at 1540-1580 deg. F., oil quench, temper 1 hr. Min.; threaded to m10x1-6g; thread lg. is 45.0 mm.

**Height:**

16.0 millimeters

**Material:**

Steel

**Material Specification:**

Astm a322, grade 4140 assn standard single material response or astm a331, grade 4140 assn standard single material response or mil-s-22141, cmpsn ic4140 military specification single material response

**Surface Treatment:**

Phosphate manganese or phosphate zinc

**Surface Treatment Specification:**

Mil-p-16232, class 1, type m orz military specification single treatment response

**Style Designator:**

Shoulder

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A212a0

**Mil-std (military Standard):**

Mil-s-22141 spec.