

View Online at <https://aerobasegroup.com/nsn/5315-01-389-6396>

First End Style:

Chamfered

Second End Style:

Radius

Pinlength:

Between 2.090 inches and 3.010 inches

Pindiameter:

Between 0.6251 inches and 0.6253 inches

Second End Corner Radius:

Between 0.078 inches and 0.208 inches

First End Taper Length:

0.750 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 42.0 rockwell c

Shear Strength:

45000 double pounds per square inch

First End Taper Angle:

Between 4.0 degrees and 16.0 degrees

Surface Finish:

16.0 microinches outside diameter

Special Features:

Hardness of 75-83hrb or equivalent for type 303 steel.

Material:

Steel comp 303 or steel comp 416 or steel comp 410

Material Specification:

Astm a582 assn standard single material response or astm a493 assn standard single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Astm a380 assn standard single treatment response

Specification Data:

96906-ms16555 government standard

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-p-21143 spec.