

View Online at <https://aerobasegroup.com/nsn/5315-01-509-0779>

First End Style:

Chamfered

Pinlength:

Between 0.580 inches and 0.590 inches

Pindiameter:

Between 0.0939 inches and 0.0941 inches

End Application:

F100/220 eng

First End Taper Length:

Between 0.005 inches and 0.015 inches

Second End Relationship With First End:

Identical

Hardness Rating:

26.0 rockwell c and 33.0 rockwell c

First End Taper Angle:

45.0 degrees

Material:

Steel comp 410

Surface Treatment:

Passivate

Surface Treatment Specification:

Bendix es 091 mfr ref single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0