

View Online at <https://aerobasegroup.com/nsn/5315-01-595-1321>

**First End Style:**

Chamfered

**Second End Style:**

Chamfered

**Overall Length:**

1.281 inches

**Undercut Diameter:**

0.228 inches

**Second End Relationship With First End:**

Not identical

**Hardness Rating:**

58.0 rockwell c and 62.0 rockwell c

**Surface Finish:**

32.0 micrometers

**Special Features:**

Used on 252137, 5586086, 6127128; magnetic particle inspection; apply protective coating per mil-p-16232 ty m cl 1, finish coat all surfaces with 0.0002-0.005 thick solid film lubricant electrofilm lube-lok no 4396 or equiv (mil-I-46010

**Material:**

Steel comp 8620

**Material Specification:**

Asteel 8620 mfr ref single material response

**Surface Treatment:**

Phosphate manganese and lubricant

**Surface Treatment Specification:**

Mil-dtl-16232 ty m cl 1 military specification single treatment response

**Style Designator:**

Groove

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A212a0

**Mil-std (military Standard):**

Mil-dtl-16232 spec.