

View Online at <https://aerobasegroup.com/nsn/5315-01-595-1321>

First End Style:

Chamfered

Second End Style:

Chamfered

Overall Length:

1.281 inches

Undercut Diameter:

0.228 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

58.0 rockwell c and 62.0 rockwell c

Surface Finish:

32.0 micrometers

Special Features:

Used on 252137, 5586086, 6127128; magnetic particle inspection; apply protective coating per mil-p-16232 ty m cl 1, finish coat all surfaces with 0.0002-0.005 thick solid film lubricant electrofilm lube-lok no 4396 or equiv (mil-I-46010)

Material:

Steel comp 8620

Material Specification:

Asteel 8620 mfr ref single material response

Surface Treatment:

Phosphate manganese and lubricant

Surface Treatment Specification:

Mil-dtl-16232 ty m cl 1 military specification single treatment response

Style Designator:

Groove

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-dtl-16232 spec.