

View Online at <https://aerobasegroup.com/nsn/5325-00-282-7116>

Cross Sectional Shape:

Rounded corners

Inside Diameter:

Between 0.251 inches and 0.258 inches

Casehardening Indicator:

Not casehardened

Major Thickness:

Between 0.024 inches and 0.027 inches

Ring Style:

External

Usage Design:

External

Material Hardness Rating:

Between 38.0 rockwell c and 40.0 rockwell c

Strength Rating:

190000.000 pounds per square inch tensile

Material:

Copper-beryllium alloy, qq-c533, condition ht

Material:

Copper-beryllium alloy, qq-c533, condition ht

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T252-g