
Retaining Ring - Page 1 of 1





Cross Sectional Shape: Rectangular Casehardening Indicator:

Not casehardened

Outside Diameter:

Between 5.420 inches and 5.550 inches

Major Thickness:

Between 0.106 inches and 0.112 inches

Ring Style:

Internal

Usage Design:

Internal

Material Hardness Rating:

Between 45.0 rockwell c and 52.0 rockwell c

Material:

Stee, fed standard 66, aisi or sae 1066 to 1090

Material:

Stee, fed standard 66, aisi or sae 1066 to 1090

Surface Treatment:

Phosphate zinc

Surface Treatment:

Phosphate, mil-p-16232, type z, class 2

Shelf Life:

N/a

Unit Of Measure:

Demilitarization:

No

Fiig:

T252-g