Retaining Ring - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5325-00-530-8078

| Beveled one ou | tside corner | | |
|-----------------|-------------------------------|--|--|
| Casehardening | | | |
| Not caseharden | | | |
| Outside Diame | | | |
| | inches and 1.274 inches | | |
| Minor Thicknes | SS: | | |
| Between 0.039 | inches and 0.041 inches | | |
| Major Thicknes | SS: | | |
| | inches and 0.052 inches | | |
| Ring Style: | | | |
| Internal | | | |
| Usage Design: | | | |
| Internal | | | |
| Material Hardn | ess Rating: | | |
| Between 44.0 ro | ockwell c and 51.0 rockwell c | | |
| Material: | | | |
| Steel corrosive | resistant, aisi 420 | | |
| Material: | | | |
| Steel corrosive | resistant, aisi 420 | | |
| Surface Treatm | nent: | | |
| Passivate | | | |
| Surface Treatm | nent: | | |
| Passivated, qq | -p-35 | | |
| Shelf Life: | | | |
| N/a | | | |
| Unit Of Measur | re: | | |
| | | | |
| Demilitarizatio | n: | | |
| No | | | |
| Fiig: | | | |
| T252-g | | | |